



WOW Marble & Granite Super Fast Adhesive

WOW Marble & Granite Super Fast Adhesive is an adhesive set consisting of high viscosity cyanoacrylate and activator, which is developed especially for bonding materials such as natural stone, marble, granite and decorative stones.

Advantages:

- Ability to bond rapidly in seconds,
- High bonding power
- Thanks to its high viscosity formula, it can be used in vertical places without pour and splash,
- Activator makes it possible and incredibly fast to bond even porous surfaces,

Usage Areas:

- Utilized in assembly and repairs of parts such as natural stone, marble, granite, wood, MDF and metal.
- Preferred especially in the applications which require rapid curing

How to use:

- One of the substrates need to be smooth and have a good connection area.
- Apply a drop on one of the substrates and use spray on the other one.
- Join substrates and press firmly for approximately one minute.
- Application temperature is between +41°F and +95°F.

Shelf Life:

12 months in unopened packaging in a dry and cool storage place at temperatures between +41°F and +77°F.

Packaging (Weight/Volume):

6,76 fl oz + 1,76 oz, 24pcs in a box.



TECHNICAL DATA SHEET

www.krakenchem.com - info@krakenchem.com

Safety

- Cyanoacrylates should ideally be stored in original sealed containers until used.
- Avoid exposure to strong light and heat sources
- Cyanoacrylates can bond to skin within seconds
- Do not drip into skin or into eyes - can cause serious injury to your eyes.
- Will become hard in container if not closed properly!
- Activator is flammable. Do not throw into fire.
- Activator box is pressured. Do not crush or drill.
- Use gloves when working.
- Do not expose to temperatures higher than +122°F.
- Keep away from direct sunlight
- Keep away from sources of ignition, no smoking.
- Keep out of the reach of children.

Physical & Chemical Properties

For Glue:

Chemical Structure: Ethyl Cyanoacrylate

Appearance: Liquid gel

Color: Colorless

Flashpoint: > 177°F

Application Temperature: +41°F to +95°F

Density: 8,85±0,1 lb/gal (ISO 1183)

Viscosity: 1200 - 1800 Cps at 77°F (ASTM D1084)

Temperature Resistance: -4°F to +158°F

For Activator:

Chemical Structure: Hexane

Appearance: Aerosol

Color: Colorless

Application Temperature: +41°F to +95°F

Temperature Resistance: -4°F to +158°F